

BRICK AND SLASTO DRESSING

PRODUCT CODE: TBD 1

TECHNICAL DATA SHEET

| Product Description | <ul style="list-style-type: none"> A solvent based UV resistant clear gloss acrylic coating. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|--------------------------------|---|---------------------|---|-------------------|-------------------------|---------------|--|------------------------------|---|-------------------------|--|---------------------|---------------------|----------------------------|--|--------------------------|---|------------------------------|---------|--|------------|------------|----------|-------------|--|-----------|----------------|-------------|-------------|---------------|-------------|
| Intended Uses | <ul style="list-style-type: none"> BRICK AND SLASTO DRESSING is a highly durable coating to enhance and protect interior and exterior face brick, slasto and ornamental stone. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Features & Benefits | <ul style="list-style-type: none"> UV resistant. Very good abrasion resistance. Brings out the natural beauty of the coated surface. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Product Information | <table> <tr> <td>Appearance</td> <td>Gloss</td> </tr> <tr> <td>Colour</td> <td>Clear</td> </tr> <tr> <td>Generic type</td> <td>Acrylic</td> </tr> <tr> <td>Solids</td> <td>Approx. 24 % by mass; 20 % by volume</td> </tr> <tr> <td>S G</td> <td>0,91 kg/ℓ (typical)</td> </tr> <tr> <td>Flash Point</td> <td>> 35 °C</td> </tr> <tr> <td>Theoretical spreading rate</td> <td>10 m²/ℓ per coat @ 20 µm. This serves as a guide only</td> </tr> <tr> <td>Practical spreading rate</td> <td>The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used.</td> </tr> <tr> <td>VOC</td> <td>695 g/ℓ</td> </tr> </table> | Appearance | Gloss | Colour | Clear | Generic type | Acrylic | Solids | Approx. 24 % by mass; 20 % by volume | S G | 0,91 kg/ℓ (typical) | Flash Point | > 35 °C | Theoretical spreading rate | 10 m ² /ℓ per coat @ 20 µm. This serves as a guide only | Practical spreading rate | The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used. | VOC | 695 g/ℓ | | | | | | | | | | | | |
| Appearance | Gloss | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Colour | Clear | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Generic type | Acrylic | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Solids | Approx. 24 % by mass; 20 % by volume | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| S G | 0,91 kg/ℓ (typical) | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Flash Point | > 35 °C | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Theoretical spreading rate | 10 m ² /ℓ per coat @ 20 µm. This serves as a guide only | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Practical spreading rate | The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| VOC | 695 g/ℓ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Application Details | <table> <tr> <td>Mixing</td> <td>Stir thoroughly with a flat paddle until homogeneous.</td> </tr> <tr> <td>Method</td> <td>Brush or airless spray.</td> </tr> <tr> <td>Thinning</td> <td>PLASCON UNIVERSAL REDUCER (PUR 1) – See Application overleaf for thinning recommendations.</td> </tr> <tr> <td>Cleaning</td> <td>PLASCON UNIVERSAL REDUCER (PUR 1).</td> </tr> <tr> <td>Application Environment</td> <td> <table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </tbody> </table> </td> </tr> <tr> <td>Drying time</td> <td> <table> <tr> <td>Touch dry</td> <td>30 min @ 23 °C</td> </tr> <tr> <td>Overcoating</td> <td>4 h @ 23 °C</td> </tr> <tr> <td>Dry to handle</td> <td>4 h @ 23 °C</td> </tr> </table> </td> </tr> </table> | Mixing | Stir thoroughly with a flat paddle until homogeneous. | Method | Brush or airless spray. | Thinning | PLASCON UNIVERSAL REDUCER (PUR 1) – See Application overleaf for thinning recommendations. | Cleaning | PLASCON UNIVERSAL REDUCER (PUR 1). | Application Environment | <table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </tbody> </table> | Surface Temperature | Ambient Temperature | Relative Humidity | Min: 10 °C | Min: 10 °C | Min: 10% | or 2 °C min. above dew point | | | Max: 40 °C | Max: 40 °C | Max: 85% | Drying time | <table> <tr> <td>Touch dry</td> <td>30 min @ 23 °C</td> </tr> <tr> <td>Overcoating</td> <td>4 h @ 23 °C</td> </tr> <tr> <td>Dry to handle</td> <td>4 h @ 23 °C</td> </tr> </table> | Touch dry | 30 min @ 23 °C | Overcoating | 4 h @ 23 °C | Dry to handle | 4 h @ 23 °C |
| Mixing | Stir thoroughly with a flat paddle until homogeneous. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Method | Brush or airless spray. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Thinning | PLASCON UNIVERSAL REDUCER (PUR 1) – See Application overleaf for thinning recommendations. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Cleaning | PLASCON UNIVERSAL REDUCER (PUR 1). | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Application Environment | <table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </tbody> </table> | Surface Temperature | Ambient Temperature | Relative Humidity | Min: 10 °C | Min: 10 °C | Min: 10% | or 2 °C min. above dew point | | | Max: 40 °C | Max: 40 °C | Max: 85% | | | | | | | | | | | | | | | | | | |
| Surface Temperature | Ambient Temperature | Relative Humidity | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Min: 10 °C | Min: 10 °C | Min: 10% | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| or 2 °C min. above dew point | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Max: 40 °C | Max: 40 °C | Max: 85% | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Drying time | <table> <tr> <td>Touch dry</td> <td>30 min @ 23 °C</td> </tr> <tr> <td>Overcoating</td> <td>4 h @ 23 °C</td> </tr> <tr> <td>Dry to handle</td> <td>4 h @ 23 °C</td> </tr> </table> | Touch dry | 30 min @ 23 °C | Overcoating | 4 h @ 23 °C | Dry to handle | 4 h @ 23 °C | | | | | | | | | | | | | | | | | | | | | | | | |
| Touch dry | 30 min @ 23 °C | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Overcoating | 4 h @ 23 °C | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Dry to handle | 4 h @ 23 °C | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Storage and Packaging | <p>Store away from direct sun, heat and severe cold.</p> <p>Packaging: 1 ℓ and 5 ℓ</p> | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Surface Preparation | <p>All surfaces must be sound, clean, dry and free from dirt, oil, grease or any other contaminants.</p> <ol style="list-style-type: none"> Remove cement stains and excess mortar with POLYCELL MORTALIFT (511001). Rinse thoroughly and allow to dry. UNCOATED BRICK, SLASTO AND STONE IN GOOD CONDITION: Remove any wax polish, oil, grease, dirt, saline deposits, etc with AQUASOLV DEGREASER (GR 1). Rinse thoroughly with clean water. Allow to dry. SURFACES PREVIOUSLY COATED WITH BRICK AND SLASTO DRESSING Remove loose and flaking material. Remove any grease, oil, etc. with AQUASOLV DEGREASER (GR 1). Rinse thoroughly with clean water. Allow to dry. WEATHERED BRICK , SLASTO AND STONE Remove all loose slivers, friable and powdery material. Brush off all loose dust. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |

BRICK AND SLASTO DRESSING

PRODUCT CODE: TBD 1

| | |
|---------------------------|---|
| Application | <ul style="list-style-type: none"> • Ready for use for application by brush and airless spray to non-porous surfaces (e.g. face brick and ornamental stone). • For normal porous surfaces thin 10 parts BRICK AND SLASTO DRESSING to 1 part UNIVERSAL REDUCER (PUR 1) by volume. • For very porous surfaces (e.g. weathered slasto) thin first coat up to 1 part BRICK AND SLASTO DRESSING to 1 part UNIVERSAL REDUCER (PUR 1) by volume. Allow 4 hours drying then apply a second coat in similar manner. • Always apply a liberal wet coat to penetrate fine cracks and porous areas. Remove bubbles that may form. • One coat is usually sufficient for non-porous surfaces such as face brick and ornamental stone. Porous surfaces require a second coat. A third coat may be necessary on exceptionally porous surfaces for best protection and appearance. • When brushing on a second coat, apply briskly and avoid "overworking" which may disturb the first coat. |
| Cautions | <ul style="list-style-type: none"> • Avoid application to hot surfaces which may cause undue bubbling. • Do not apply over other types of brick dressings or varnishes unless compatibility has been established beforehand. • Not recommended for surfaces where moisture may be absorbed from behind, such as unsealed flower boxes. • Roller application not recommended since it may cause undue bubbling. |
| Safety Precautions | <ul style="list-style-type: none"> • Always keep paint out of reach of children. • Ensure good ventilation during application and drying. • If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner. • Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention. • Harmful if swallowed. Seek medical attention and do not induce vomiting. • Do not smoke while painting. • Flammable. Store in a cool dry place away from heat and sparks. • Refer to Material Safety Data Sheet for complete information. |

DISCLAIMER:

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

N.B. Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

N.B. TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED:

CAPE TOWN:

P O Box 42
Eppindust 7475
Tel: (021) 505-2400
Fax: (021) 534-3791

DURBAN:

Private Bag X16
Mobeni 4060
Tel: (031) 451-3200
Fax: (031) 451-3411

GAUTENG:

P.O. Box 4010
Luipaardsvlei 1743
Tel: (011) 951-4500
Fax: (011) 955-2841

PORT ELIZABETH:

P O Box 1594
Port Elizabeth 6000
Tel: (041) 401-1400
Fax: (041) 453-4606

PLASCON ADVISORY SERVICE: 0860 20 40 60