

EASY LIVING GLOSS ENAMEL

PRODUCT CODE: ELE Range

TECHNICAL DATA SHEET

Product Description	A high quality solvent based enamel with a high gloss finish.														
Intended Uses	Used as a decorative and protective finish on interior and exterior mild steel, galvanised steel, timber and masonry.														
Features	<ul style="list-style-type: none"> • Dries to a tough durable finish with good weather resistance. • Advanced formulation • Flawless polished finish. • Lead free. • 7 year Quality Guarantee, Interior only (Refer to T's & C's at www.plascon.co.za) 														
Product Information	Appearance	High gloss													
	Colours	White (ELE 1) and standard colours as per colour card. Also available in a wide range of INSPIRED COLOUR tints:													
	Tint Bases	Pastel (ELE 1000), Deep (ELE 2000), Transparent (ELE 3000)													
	Volume Solids	49% (typical for white)													
	Recommended DFT	25 – 35 µm per coat													
	Recommended WFT	51 – 71 µm per coat													
	Theoretical spreading rate	16.3 m ² /L @ 30 µm DFT. This serves as a guide only.													
	Practical spreading rate	The practical spreading rate will vary depending on the profile of the substrate, as well as the application technique and tools used.													
	TVOC	381 g/L for White. < 415 g/L for Tint bases													
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous and stir periodically during use.													
	Method	Brush, roller or spray.													
	Thinning	Not normally necessary to thin for brush or roller application. For Spray Application thin approx. 10 parts EASY LIVING GLOSS ENAMEL to 1 part SPRAYING THINNER (TH 3) or MINERAL TURPENTINE (AZH 1) by volume.													
	Cleaning	MINERAL TURPENTINE (AZH 1) or POLYCELL BRUSH CLEANER													
	Drying time	Touch dry: 4 h @ 23 °C Over coating: 16 h @ 23 °C													
	Application Environment	<table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 35 °C</td> <td>Max: 35 °C</td> <td>Max: 85 %</td> </tr> </tbody> </table>		Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	or 2 °C min. above dew point			Max: 35 °C	Max: 35 °C	Max: 85 %
Surface Temperature	Ambient Temperature	Relative Humidity													
Min: 10 °C	Min: 10 °C	Min: 10%													
or 2 °C min. above dew point															
Max: 35 °C	Max: 35 °C	Max: 85 %													
Storage and Packaging	Store away from direct sun, heat and severe cold. Packaging: 1 L and 5 L														
Tint bases	<ul style="list-style-type: none"> • The tint base containers are under filled to levels which are specific for the tint base to allow for a calculated volume of colourants to be added. The volume indicated on the container is only achieved after the addition of all prescribed colourants as per the formulation. • The tint base and the colourants are unfinished intermediate products which are not recommended for use individually. A finished product is only produced once the prescribed quantities of colourants have been thoroughly mixed with the tint base. • When mixed to a finished product its technical features, product information, application and surface preparation details comply with that of EASY LIVING GLOSS ENAMEL. • Only colourants from the PLASCON INSPIRED COLOUR system are permitted for use when tinting 														

EASY LIVING GLOSS ENAMEL

PRODUCT CODE: ELE Range

Tinting Procedure	<ul style="list-style-type: none"> Select the required colour and reference no. from the PLASCON INSPIRED COLOUR fandeck, other suitable fandecks or colour cards and locate the applicable formulation from the tables. Certain colour choices may require more than two coats to achieve full obliteration, (see computer formulations for details in remark column prior to tinting). Select the required tint base and volume for tinting and set the tinting machine to deliver the correct amount of colourants as per formulation. Inject all required colourants, close container and shake on mechanical shaker for 5 minutes. Note: UNDER NO CIRCUMSTANCES MUST COLOURS BE TINTED FROM EASY LIVING GLOSS ENAMEL WHITE (ELE 1), USE ONLY THE PRESCRIBED TINT BASE.
Surface Preparation	<p>Ensure that surfaces are dry, sound and free from dust, dirt, grease and oil before painting. Allow 16 hours drying time to all primed surfaces before applying topcoat.</p> <p>NEW WORK:</p> <p>1. NEW WORK:</p> <p>1.1 Cement plaster, concrete, gypsum plaster (e.g. Rhinolite, Creststone), gypsum board, e.g. Rhinoboard), and unglazed brick: Prime entire area with PLASCON PLASTER PRIMER (UC 56)</p> <p>1.2 Fibre-cement: Prime with PLASCON MULTI SURFACE PRIMER (WUP 1)</p> <p>1.3 Wood: Sand until smooth in the direction of the grain and dust off. Seal knots with WOODCARE KNOT SEAL (PK 2), then prime with PLASCON WOOD PRIMER (UC 2).</p> <p>1.4 Mild steel: Degrease with AQUASOLV DEGREASER (GR 1) and rinse thoroughly with water until water runs freely off the surface. Remove any rust by wire brushing. Prime with PLASCON METALCARE MILD STEEL PRIMER (UC 501)</p> <p>1.5 Galvanised steel: Clean with PLASCON METALCARE GALVANISED IRON CLEANER (GIC 1) and rinse thoroughly with water until water runs freely off the surface. Prime with PLASCON METALCARE GALVANISED IRON PRIMER (GIP 1).</p> <p>2 PREVIOUSLY PAINTED SURFACES:</p> <p>2.1 Previously painted surfaces in good condition: Remove loose and flaking paint by scraping and sanding. Clean with POLYCELL SUGAR SOAP POWDER solution to remove all contaminants and chalked material. Rinse well with clean water to remove all traces of SUGAR SOAP. Alternatively, clean with high pressure water jet. Spot prime bare areas with the appropriate primer. Sand glossy enamel surfaces to a matt finish and apply a coat of PLASCON UNIVERSAL UNDERCOAT (UC 1).</p> <p>2.2 Previously painted surfaces in poor condition: Completely remove paint by most appropriate means e.g. scraping, coarse sanding or removing with REMOVALL ALL PURPOSE COATINGS REMOVER (RRA 220). Proceed as for new work.</p> <p>3 FILLING: Cracks: Fill defects with the appropriate POLYCELL POLYFILLA. Wood and fibre-cement: Fill with POLYCELL MENDALL 90.</p> <p>4 UNDERCOAT: Apply PLASCON UNIVERSAL UNDERCOAT (UC 1) to all prepared and primed surfaces as above.</p>
Application	<ul style="list-style-type: none"> Ready for use with brush or roller application. For spray application thin as recommended. Apply two or more coats to achieve complete obliteration
Cautions	<ul style="list-style-type: none"> Not recommended for areas where chemical resistance is required. Heavy applications (exceeding 35 µm DFT) should be avoided to prevent wrinkling. To ensure that colours on a project are consistent check that product codes and batch numbers are the same.
Safety Precautions	<ul style="list-style-type: none"> Always keep paint out of reach of children. Ensure good ventilation during application and drying. If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner. Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention. Harmful if swallowed. Seek medical attention and do not induce vomiting. Do not smoke while painting. Flammable. Store in a cool dry place away from heat and sparks. Refer to Safety Data Sheet for complete information.



EASY LIVING GLOSS ENAMEL

PRODUCT CODE: ELE Range

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,
Factoria, Krugersdorp
South Africa
1739.

Tel: +27 11 951 4500

Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za

