

PLASCON TILE & MELAMINE PRIMER

PRODUCT CODE: CTP 1

TECHNICAL DATA SHEET

Product Description	A high performance water-based acrylic primer for interior ceramic wall tiles & melamine surfaces														
Intended Uses	<ul style="list-style-type: none"> Promotes adhesion to ceramic wall tiles and melamine before painting with enamel or emulsion topcoats, thereby allowing kitchens and bathrooms to be transformed without the cost and upheaval of re-tiling or replacing cupboards. 														
Features	<ul style="list-style-type: none"> A versatile white water-based primer for use on ceramic wall tiles and melamine. Specifically for interior use. May be overcoated with solvent based decorative enamels and water-based emulsion paints. Single pack, water-based and low odour. 														
Product Information	Appearance	Matt													
	Colour	White													
	Solids	Approx. 58 % by mass; 43 % by volume													
	S G	1,33 (typical)													
	Viscosity at 23 °C	Approx. 88 KU													
	Recommended DFT	Min: 20 µm Max: 35 µm													
	Theoretical spreading rate	17 m ² /ℓ per coat at 25 µm DFT. This serves as a guide only													
	Flash point	Non-flammable													
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous.													
	Method	Brush, roller or spray.													
	Thinning	Not recommended.													
	Cleaning	Water													
	Substrate	Well prepared ceramic tiles and melamine.													
	Application Environment	<table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </tbody> </table>		Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	or 2 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85%
Surface Temperature	Ambient Temperature	Relative Humidity													
Min: 10 °C	Min: 10 °C	Min: 10%													
or 2 °C min. above dew point															
Max: 40 °C	Max: 40 °C	Max: 85%													
	Drying time	Touch dry 1 h at 23 °C Over coating with water-based topcoats: 4 h at 23 °C with solvent based topcoats: 24 h at 23 °C N.B. Allow longer recoating times in cool and wet weather conditions.													
Storage and Packaging	Store away from direct sun, heat and severe cold. Packaging: 1 ℓ plastic container.														

PLASCON TILE & MELAMINE PRIMER

PRODUCT CODE: CTP 1

Surface Preparation	<p>Ensure that surfaces are dry, sound and free from dust, dirt, grease and oil before painting. Fill defects with the appropriate POLYCELL POLYFILLA filler. For best results replace all cracked, broken or chipped tiles.</p> <ol style="list-style-type: none"> Ceramic tiles and Melamine (unpainted): Remove any oil and greasiness with POLYCELL SUGAR SOAP POWDER solution and scouring pad. For firmly adherent cooking oils in kitchen areas use AQUASOLV DEGREASER (GR 1). Rinse thoroughly with water. Allow to dry. Ceramic tiles and Melamine (previously painted in good condition): Clean tile surfaces with POLYCELL SUGAR SOAP POWDER solution and scouring pad. Rinse thoroughly with fresh water to remove all traces of sugar soap. Allow to dry. Sand melamine surfaces lightly with medium to fine paper to provide a key. Dust off. Ceramic tiles and Melamine (previously painted in poor condition): Remove loose and flaking paint with REMOVAL ALL PURPOSE COATINGS REMOVER (RRA 220) or by scraping and sanding, then cleaning with POLYCELL SUGAR SOAP POWDER solution. Rinse thoroughly with fresh water. Allow to dry. N.B: For warm humid conditions, such as bathrooms and kitchens, use VELVAGLO (VLO) or KITCHENS & BATHROOMS PAINT (KBM 1) as topcoats.
Application	<ul style="list-style-type: none"> Apply a full wet coat by brush, mohair roller or spray. For best results, apply two coats of TILE & MELAMINE PRIMER. Allow the first coat to dry thoroughly, then sand lightly with a fine paper and wipe clean before applying the second coat. Sand the primed surface lightly before application of the topcoat.
Cautions	<ul style="list-style-type: none"> Not recommended for use in showers. Avoid painting in damp conditions or if the temperature is below 10 °C. Not recommended for floors, kitchen work surfaces and glass mosaics.
Safety Precautions	<ul style="list-style-type: none"> Keep out of reach of children. Ensure good ventilation during application and drying. In case of skin contact, wash with soap and water or a recognised skin cleaner. Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist. Harmful if swallowed. Do not induce vomiting. Seek medical attention. Refer to Material Safety Data Sheet for complete information.

DISCLAIMER:

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

N.B. Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LTD

CAPE TOWN:

P. O Box 42
Eppindust 7475
Tel: (021) 505-2400
Fax: (021) 534-3791

DURBAN:

Private Bag X16
Mobeni 4060
Tel: (031) 451-3200
Fax: (031) 451-3411

GAUTENG:

P.O. Box 4010
Luipaardsvlei 1743
Tel: (011) 951-4500
Fax: (011) 955-2841

PORT ELIZABETH:

P. O. Box 1594
Port Elizabeth 6000
Tel: (041) 401-1400
Fax: (041) 453-4606

PLASCON ADVISORY SERVICE: 0860 20 40 60

