

NATURAL DECK COATING

PRODUCT CODE: WWV RANGE

TECHNICAL DATA SHEET

Product Description	<ul style="list-style-type: none"> Premium quality water based deck coating for exterior use. 																																
Intended Uses	<ul style="list-style-type: none"> To seal and protect exterior wooden surfaces such as decks, outdoor wood furniture, wooden bridges and docks, garage doors, shutters, window frames, doors, garden furniture, gates etc. 																																
Features & Benefits	<ul style="list-style-type: none"> Water based, Easy to apply Penetrates and rejuvenates wood Low odour and low VOC Built in UV stabilisers and preservatives to protect and increase the lifespan of wooden materials Seals and protects against moisture Excellent wear resistance Low-build finish that maintains the natural appearance of wood Can be used on all wood types (SA Pine, Meranti, Ballau, Saligna) 																																
Product Information	<table> <tr> <td>Appearance</td> <td>Clear (WWV 1) - milky in wet state but dries to a clear</td> </tr> <tr> <td>Colours</td> <td>Light Oak (WWV 2), Teak (WWV 3), Oregon (WWV 4), Imbuia (WWV 5) and Mahogany (WWV 6)</td> </tr> <tr> <td>Solids</td> <td>Approx. 15% by mass; 12 % by volume</td> </tr> <tr> <td>S G at 23°C</td> <td>1,040 kg/ℓ (typical)</td> </tr> <tr> <td>VOC</td> <td><16g/ℓ</td> </tr> <tr> <td>Flash Point</td> <td>Non Flammable</td> </tr> <tr> <td>Theoretical spreading rate</td> <td>10-15 m²/ℓ per coat. This serves as a guide only.</td> </tr> <tr> <td>Practical spreading rate</td> <td>The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used.</td> </tr> </table>	Appearance	Clear (WWV 1) - milky in wet state but dries to a clear	Colours	Light Oak (WWV 2), Teak (WWV 3), Oregon (WWV 4), Imbuia (WWV 5) and Mahogany (WWV 6)	Solids	Approx. 15% by mass; 12 % by volume	S G at 23°C	1,040 kg/ℓ (typical)	VOC	<16g/ℓ	Flash Point	Non Flammable	Theoretical spreading rate	10-15 m ² /ℓ per coat. This serves as a guide only.	Practical spreading rate	The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used.																
Appearance	Clear (WWV 1) - milky in wet state but dries to a clear																																
Colours	Light Oak (WWV 2), Teak (WWV 3), Oregon (WWV 4), Imbuia (WWV 5) and Mahogany (WWV 6)																																
Solids	Approx. 15% by mass; 12 % by volume																																
S G at 23°C	1,040 kg/ℓ (typical)																																
VOC	<16g/ℓ																																
Flash Point	Non Flammable																																
Theoretical spreading rate	10-15 m ² /ℓ per coat. This serves as a guide only.																																
Practical spreading rate	The practical spreading rate will vary depending on the porosity and profile of the substrate, as well as the application technique and tools used.																																
Application Details	<table> <tr> <td>Mixing</td> <td>Stir thoroughly with a flat paddle until homogeneous.</td> </tr> <tr> <td>Substrate</td> <td>Well prepared wood surfaces.</td> </tr> <tr> <td>Method</td> <td>Brush.</td> </tr> <tr> <td>Thinning</td> <td>Not recommended. Ready for use</td> </tr> <tr> <td>Cleaning</td> <td>Water</td> </tr> <tr> <td>Application Environment</td> <td> <table border="1"> <tr> <td>Surface Temperature</td> <td>Ambient Temperature</td> <td>Relative Humidity</td> </tr> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </table> </td> </tr> <tr> <td>Drying time</td> <td> <table> <tr> <td>Touch dry</td> <td>30 min at 23 °C</td> </tr> <tr> <td>Dry to handle</td> <td>4 h at 23 °C</td> </tr> <tr> <td>Over coating</td> <td>4 h at 23 °C</td> </tr> </table> </td> </tr> </table>	Mixing	Stir thoroughly with a flat paddle until homogeneous.	Substrate	Well prepared wood surfaces.	Method	Brush.	Thinning	Not recommended. Ready for use	Cleaning	Water	Application Environment	<table border="1"> <tr> <td>Surface Temperature</td> <td>Ambient Temperature</td> <td>Relative Humidity</td> </tr> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	or 2 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85%	Drying time	<table> <tr> <td>Touch dry</td> <td>30 min at 23 °C</td> </tr> <tr> <td>Dry to handle</td> <td>4 h at 23 °C</td> </tr> <tr> <td>Over coating</td> <td>4 h at 23 °C</td> </tr> </table>	Touch dry	30 min at 23 °C	Dry to handle	4 h at 23 °C	Over coating	4 h at 23 °C
Mixing	Stir thoroughly with a flat paddle until homogeneous.																																
Substrate	Well prepared wood surfaces.																																
Method	Brush.																																
Thinning	Not recommended. Ready for use																																
Cleaning	Water																																
Application Environment	<table border="1"> <tr> <td>Surface Temperature</td> <td>Ambient Temperature</td> <td>Relative Humidity</td> </tr> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	or 2 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85%																				
Surface Temperature	Ambient Temperature	Relative Humidity																															
Min: 10 °C	Min: 10 °C	Min: 10%																															
or 2 °C min. above dew point																																	
Max: 40 °C	Max: 40 °C	Max: 85%																															
Drying time	<table> <tr> <td>Touch dry</td> <td>30 min at 23 °C</td> </tr> <tr> <td>Dry to handle</td> <td>4 h at 23 °C</td> </tr> <tr> <td>Over coating</td> <td>4 h at 23 °C</td> </tr> </table>	Touch dry	30 min at 23 °C	Dry to handle	4 h at 23 °C	Over coating	4 h at 23 °C																										
Touch dry	30 min at 23 °C																																
Dry to handle	4 h at 23 °C																																
Over coating	4 h at 23 °C																																
Storage & Packaging	<p>Store away from direct sun, heat and severe cold.</p> <p>Packaging: 1 ℓ and 5 ℓ .</p>																																

NATURAL DECK COATING

PRODUCT CODE: WWV Range

Surface Preparation	<p>All surfaces must be clean, dry and sound. Remove any oil, grease, mortar droppings, etc.</p> <ol style="list-style-type: none"> NEW WOOD: Sand in the direction of the grain, to a smooth finish with 150 grit paper. Remove dust with a damp cloth. PREVIOUSLY VARNISHED WOOD IN GOOD CONDITION: Sand to a Matt finish to create a key. Remove dust with a damp cloth. PREVIOUSLY VARNISHED WOOD IN BAD CONDITION: Remove old varnish by sanding or by using REMOVAL ALL PURPOSE PAINT REMOVER (RRA 220). The treated surface must be rinsed with water to remove all chemical residues before re-coating. Sand to a smooth finish. Remove dust with a damp cloth. WOOD PREVIOUSLY COATED WITH WAX SEALER/OIL BASED WOOD PRESERVATIVE: Remove all evidence of residue by Mechanically sanding or by using REMOVAL ALL PURPOSE PAINT REMOVER (RRA 220). Remove dust with a damp cloth. PREVIOUSLY PAINTED WOOD: Strip old paint by deep sanding or by using REMOVAL ALL PURPOSE PAINT REMOVER (RRA 220). Rinse thoroughly with fresh water. Sand bare wood to a smooth finish. Remove dust with a damp cloth. DISCOLOURED OR WEATHERED WOOD: Remove discoloured or weathered layer by sanding with 100 grit paper. Sand bare wood to a smooth finish with 150 grit paper. Remove dust with a damp cloth. KNOTS IN WOOD: Apply Plascon WOODCARE KNOT SEAL (PK 2). FILLER: If required use POLYCELL WOODFILLER. Sand to a smooth finish.
Application	<ul style="list-style-type: none"> Do not apply in a dusty environment. NOTE: Do not thin NATURAL DECK COATING - ready for use. Apply the first coat by brush. Allow to dry for 4 hours. Repeat second and third coats in the same manner. Apply at least 3 coats to new and old wood. Sand lightly between coats with fine paper to de-nib. Remove dust with damp cloth.
Caution	<ul style="list-style-type: none"> When coating exterior wood special attention must be given to the adequate sealing and coating of the end grain. NB: Freshly painted windows, doors and gates must be allowed to dry for at least 12 hours at 23 °C before closing. Exterior wood subject to severe climatic conditions and un-seasonal weather should be re-coated every 1 – 2 years to prevent substrate degradation.
Safety Precautions	<ul style="list-style-type: none"> Always keep paint out of reach of children. Ensure good ventilation during application and drying. If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner. Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention. Harmful if swallowed. Seek medical attention and do not induce vomiting. Refer to Material Safety Data Sheet for complete information.

DISCLAIMER:

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

CAPE TOWN:

P O Box 42
Eppindust 7475
Tel: (021) 505-2400
Fax: (021) 534-3791

DURBAN:

Private Bag X16
Mobeni 4060
Tel: (031) 451-3200
Fax: (031) 451-3411

GAUTENG:

P.O. Box 4010
Luipaardsvlei 1743
Tel: (011) 951-4500
Fax: (011) 955-2841

PORT ELIZABETH:

P O Box 1594
Port Elizabeth 6000
Tel: (041) 401-1400
Fax: (041) 453-4606

PLASCON ADVISORY SERVICE: 0860 20 40 60

