

WOODCARE SANDING SEALER

PRODUCT CODE: SS 16

TECHNICAL DATA SHEET

Product Description	A nitrocellulose based semi matt sanding sealer													
Intended Uses	<ul style="list-style-type: none"> For use as a base coat on interior wood. This specially designed material is intended for filling of grain on all interior solid timber or veneers prior to over coating with varnishes. 													
Features & Benefits	<ul style="list-style-type: none"> Excellent grain filling and sanding properties for a perfectly smooth finish Quick drying 													
Product Information	Colour	Clear												
	Solids	Approx. 17 % by mass; 12,3 % by volume												
	Viscosity at 23 °C	25 Sec FC4 (typical)												
Application Details	Mixing	Stir thoroughly with a flat paddle until homogeneous.												
	Method	Brush or spray (airless or conventional)												
	Thinner	LACQUER THINNER (ILS 1)												
	Cleaning	LACQUER THINNER (ILS 1)												
	Drying Times	Touch dry: 30 mins Over coating: 1 h @ 23 °C												
	Application Environment	<table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min: 10 °C</td> <td>Min: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max: 40 °C</td> <td>Max: 40 °C</td> <td>Max: 85%</td> </tr> </tbody> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min: 10 °C	Min: 10 °C	Min: 10%	or 2 °C min. above dew point			Max: 40 °C	Max: 40 °C	Max: 85%
Surface Temperature	Ambient Temperature	Relative Humidity												
Min: 10 °C	Min: 10 °C	Min: 10%												
or 2 °C min. above dew point														
Max: 40 °C	Max: 40 °C	Max: 85%												
Storage & Packaging	Store away from direct sun, open flames, sparks and severe cold. Packaging: 1L and 5L.													
Surface Preparation	<ul style="list-style-type: none"> Wood must be dry, firm, clean and free of contaminants. Sand wood surfaces to a smooth finish with 150 grit sand paper working in the direction of the grain. Dust down thoroughly with a damp cloth. 													
Application	<ul style="list-style-type: none"> Ready for use by brush application. For application by conventional spray and airless spray equipment thin approx. 10 % with LACQUER THINNER (ILS 1). Recommended application viscosity 17 - 20 Sec FC4 Apply first coat. Allow to dry as directed under drying times. If a second coat is required, sand first coat lightly with 280/320 grit sand paper. Dust off with a damp cloth. 													
Cautions	<ul style="list-style-type: none"> Use only recommended thinner. Ensure wood is completely dry before sealing to prevent "whitening". 													

WOODCARE SANDING SEALER

PRODUCT CODE: SS 16

Safety Precautions

- Always keep paint out of reach of children.
 - Ensure good ventilation during application and drying.
 - If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner.
 - Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention.
 - Harmful if swallowed. Seek medical attention and do not induce vomiting.
 - Do not smoke while painting.
 - Flammable. Store in a cool dry place away from heat and sparks.
 - Refer to Safety Data Sheet for complete information.
-

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

NB: TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

10 Frederick Cooper Drive,
Factoria, Krugersdorp
South Africa
1739.

Tel: +27 11 951 4500

Fax: +27 800 110 932

PLASCON ADVISORY SERVICE: 0860 20 40 60

EMAIL: advice@kansaiplascon.co.za